



StarLube™ 5442

Slightly cationic polypropylene emulsion

Product Description

StarLube™ 5442 is a slightly cationic polypropylene emulsion that is used to provide lubricity to fiberglass. It is a film former that protects the fiberglass from self-abrasion and also provides excellent fiber-to-fiber and fiber-to-metal lubricity. **StarLube™** 5442 also has good cohesion properties.

Special Properties

- Compatible with many cationic and most anionic agents that may be used in the fiberglass process.

Typical Physical Properties*

Appearance.....opalescent liquid
Color.....tan to brown
Specific Gravity.....0.95
Ionicity.....cationic
pH (100%).....9.0–10.0
Odor.....mild/bland
Viscosity (Brookfield).....<500 cps
% Solids.....31.0–33.0
Solubility.....dispersible in water

** These items are provided as general information only. They are approximate values and are not considered part of the product specifications.*

Application

StarLube™ 5442 may be used in varying concentrations to desired end use. Suggested levels of 1% to 5% owb in pad and spray applications, then dried to enhance film forming properties.

Storage

StarLube™ 5442 has excellent storage stability. It is resistant to scorching at high temperatures.

StarChem, LLC · 10150 Greenville Highway · Wellford, SC 29385 · Phone: 1-800-677-3500

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written, or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by StarChem. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release StarChem from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contain herein is unauthorized and shall not bind StarChem. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.